

MOTIV FACTORY FINISH	BALL SPINNER	RESURFACING MACHINE
1000 GRIT LSS	500x2 / 1000	500x3
2000 GRIT LSS	500 / 1000 / 1500x2	500x2 / 1000x2
3000 GRIT LSS	500 / 1000 / 2000	500 / 2000x2
4000 GRIT LSS	500 / 1000 / 2000 / 4000	500 / 2000x3
5000 GRIT LSS	500 / 1000 / 2000 / 4000x2	500 / 1000 / 2000 / 4000
5000 GRIT LSP	500 / 1000 / 2000 / POLISHx2	500 / 1000 / POLISHx2
5500 GRIT LSP	500 / 1000 / 2000 / 4000x2 / POLISH	500 / 1000 / 2000 / 4000 / POLISH

The MOTIV® Factory Finish is now rated with a final Laser Scan (LS) Grit target. Some of our finishing processes end with Sanding (S) and some end with a Polish (P). Therefore, you will see either LSS or LSP after the grit rating.

When finishing with a ball spinner, each step above is performed for 15 seconds on each station. Where you see "x2", the process is 30 seconds.

When finishing with a ball resurfacing machine, each step above is performed for 30 seconds. Where you see "x2", the process is 60 seconds, and "x3" is 90 seconds.